

TEST REPORT NUMBER: SZHJ148251

APPLICANT: GUANGZHOU PLATO PLASTIC CO. , LTD DATE: Sep 10, 2007

DAYUAN VILLAGE HENGLI TOWN NANSHA DISTRICT GUANGZHOU CITY GUANGDONG

CHINA

ATTN: 郭隆胜

SAMPLE DESCRIPTION:

ONE(1) PIECE OF SUBMITTED SAMPLE SAID TO BE 180Z PVC TARPAULIN(WHITE).

COUNTRY OF ORIGIN : CHINA.

: PLATO PLASTIC CO,.LTD. VENDOR

TESTS CONDUCTED:

AS REQUESTED BY THE APPLICANT, FOR DETAILS REFER TO ATTACHED PAGE(S) ************************

CONCLUSION:

TESTED SAMPLES STANDARD RESULT

EN71 PART 2 : 2006 EXCLUDING SUBMITTED SAMPLE SEE REMARK

CLAUSE 4.1 SURFACE FLASH

FLAMMABILITY TEST

EN71 PART 3 : 1994 AND PASS

AMENDMENT A1: 2000 AND

AC : 2002

REMARK: THE EN71-2:2006 FLAMMABILITY TEST IS APPLY TO FINISHED TOY

PRODUCT. THIS TEST IS FOR REFERENCE ONLY.

AUTHORIZED BY:

FOR INTERTEK TESTING SERVICES

SHENZHEN LTD.

BEN N.L. LIN

GENERAL MANAGER



TEST REPORT NUMBER: SZHJ148251

TESTS CONDUCTED

1 FLAMMABILITY TEST

WITH REFERENCE TO EUROPEAN STANDARD ON SAFETY OF TOYS EN71 PART 2:

CLAUSE	TESTING ITEMS	ASSESSMENT
4.1	GENERAL	P
4.2	TOYS TO BE WORN ON THE HEAD	NA
4.3	TOY DISGUISE COSTUMES AND TOYS INTENDED TO BE WORN BY A CHILD IN PLAY	NA
4.4	TOYS INTENDED TO BE ENTERED BY A CHILD	NA
4.5	SOFT FILLED TOYS WITH A PILED OR TEXTILE SURFACE	NA

REMARK : P = PASS NA = NOT APPLICABLE

DATE SAMPLE RECEIVED : SEP 03, 2007 TESTING PERIOD : SEP 03, 2007 TO SEP 05, 2007

2 TOXIC ELEMENTS ANALYSIS

AS PER EUROPEAN STANDARD ON SAFETY OF TOYS EN71 PART 3: 1994 AND AMENDMENT A1: 2000 AND AC: 2002, ACID EXTRACTION METHOD WAS USED AND TOXIC ELEMENTS CONTENT WERE DETERMINED BY INDUCTIVELY COUPLED ARGON PLASMA SPECTROMETRY.

		LIMIT
	RESULT IN mg/kg	mg/kg
SOL. BARIUM (Ba)	21	1000
SOL. LEAD (Pb)	<5	90
SOL. CADMIUM (Cd)	<5	75
SOL. ANTIMONY (Sb)	<5	60
SOL. SELENIUM (Se)	<5	500
SOL. CHROMIUM (Cr)	<5	60
SOL. MERCURY (Hg)	<5	60
SOL. ARSENIC (As)	<2.5	25

SOL. = SOLUBLE

< = LESS THAN

mg/kg = MILLIGRAM PER KILOGRAM

END OF REPORT